

ZAPPA

GLAZED PORCELAIN. Rectified. 24x48



"Inspiration is needed in geometry. Just as much as in poetry"


ALEXANDER PUSHKIN




STONE

24x48 inches

Smoke



Earth



Cream



Snow



DCOF >0,60

Matt
Colour body
Shade variation v2
Thickness 10.5 mm

SOFT

24x48 inches

Coffee



Ash



Bone



White





DCOF >0,43

Matt
Colour body
Shade variation v2
Thickness 10.5 mm

Rectangular bases available in 24x48, 24x24, 12x24 and 35x35 inches

Dimensions and technical specifications in page 39. Finishing details in pages 40 and 41





Always check with physical samples before you make a choice.

TECHNICAL SPECIFICATIONS

STONE


Absortion group (ISO 13006)	Bla
Shade variations	v2
Different design number	12
Abrasion resistance. PEI. UNE EN ISO 104545-7	4
Water absortion UNE EN ISO 10545-3	≤ 0.5
Breaking strenght (N/mm2) UNE EN ISO 104545-4	>1300 N
Flexural tensile strenght (N/mm2) UNE EN ISO 10545-3	≥ 35 N/mm2
Scratch hardness. Mohs. UNE EN ISO 67-101-92 8	9
Body colour	

SOFT

Absortion group (ISO 13006)	Bla
Shade variations	v2
Different design number	16
Abrasion resistance. PEI. UNE EN ISO 104545-7	4
Water absortion UNE EN ISO 10545-3	≤ 0.5
Breaking strenght (N/mm2) UNE EN ISO 104545-4	>1300 N
Flexural tensile strenght (N/mm2) UNE EN ISO 10545-3	≥ 35 N/mm2
Scratch hardness. Mohs. UNE EN ISO 67-101-92 8	5
Body colour	

DIMENSIONAL REQUIREMENTS

Thickness (ISO 10545-2)	± 5%
Length and width (ISO 10545-2)	± 0,6%
Surface flatness (ISO 10545-2)	± 0,5%



STONE

STONE SMOKE

STONE EARTH

STONE SNOW

STONE CREAM




SOFT


SOFT COFFEE

SOFT ASH

SOFT WHITE




SOFT BONE



MOMO
Collection

US Edition 2021



www.momocollection.info
contact@momocollection.info